

STRAPPING UMREIFUNGSBÄNDER



LINDER

Since 1951

LINDER GmbH
Hanomagstr. 22
21244 Buchholz i.d.N.

Delivery adress: Fendtstr. 1
21244 Buchholz i.d.N.
Deutschland/Germany

Fon: + 49 (0) 4181 - 92 88 - 400
info@linder-strapping.com
www.linder-strapping.com

DATA SHEET DATENBLATT

DESCRIPTION BESCHREIBUNG

LINDER steel strap

LINDER Stahlband

CHART GRAFIK



TECHNICAL SPECIFICATION TECHNISCHE DATEN

Article number Artikelnummer	3208SWSTBL
Strap width Bandbreite	32 ± 0,15 mm
Strap thickness Bandstärke	0,80 ± 0,03 mm
Quality Qualität	standardStandard
Compensation Vergütung	blue-annealed gebläut & gewachst
Winding Wicklung	ribbon winding Scheibenwicklung
Coil weight Rollengewicht	~ 50 kg
Coil inner diameter Kern-Innendurchmesser	~ 300 mm
Coil outer diameter Kern-Außendurchmesser	~ 580 mm
Meters/kg Meter/kg	~ 5,0 m/kg
Tensile strength Zugfestigkeit	750-815 N/mm ²
Nominal elongation Nominaldehnung	8 %
Make up Aufmachung	650 kg/pallet kg/Palette
Date of issue Datum der Ausstellung	26.11.2024

The right of amendments without announcement is reserved. Any responsibility, esp. for special application or patent violation cannot be derived. Only strapping with the term "UV" are particularly protected against the influence of ultraviolet radiation. For questions concerning Product liability the general terms and conditions of the Linder GmbH apply.

Das Recht auf Änderung ohne Ankündigung ist vorbehalten. Eine Haftung welcher Art auch immer, insbesondere für einen bestimmten Einsatzzweck, oder für Patentverletzungen kann daraus nicht abgeleitet werden. Nur Bänder mit der Bezeichnung „UV“ sind besonders gegen den Einfluss von ultravioletter Strahlung geschützt! Bei Produkthaftpflichtfragen gelten die Allgemeinen Geschäftsbedingungen der Linder GmbH.