

GATARIĆ d.o.o. Ul. Kninska 48
74400 Derventa Bosna i Hercegovina

Tel : +387 53 315 000
Fax : +387 53 315 001

PIB : 400147210003
JIB : 4400147210003
Matični broj : 1809741

Upis u sudski registar br. 85-01-0075-08
Upisani i uplaćeni kapital : 2.925.686.00 KM

EORI number : SIBA005005LC03846

GATARIĆ
group

www.gataric.net
komercijala@gataric.net

Nova Banka Dobo
UniCredit Bank dd

5550080000786975
3383902266134247



Glue stick Technical Data - TTO 405154

Inspection details

Inspection Items	Standard Demand	Test result	Result
Appearance	Put the samples in the transparent container, There won't be mechanical stuff in the normal light	milky color not changed	Qualified
Solid Content	≥17% a laboratory test	0.173	Qualified
Viscosity	≥ 4000mpa.s	The Viscosity is 4070mpa.s	Qualified
Cold-Melt Test	Put the samples in the -10°C fridge for 16 hours take it out in the normal room temperature then Put the samples in the 50°C constant temperature petri dish for 4 hours , then take it out ,there is no coagulum in the glue ,the glue color and viscosity cannot be changed	The glue is not solidified The white glue viscosity and color are not changed not degenerative	Qualified
Net Content	the bottle and all the assessories weight (15.47±0.5) g, the total weight with the glue is 115.47g ,the standard demand total weight is above 115.47g /pc	the lower net weight is 100.50g the higher net weight is 102g	up to standard
PH Value	06.06.08	6.6	Qualified

Date: January 2023

