

GATARIĆ d.o.o. Ul. Kninska 48
74400 Derventa Bosna i Hercegovina

Tel : +387 53 315 000
Fax : +387 53 315 001

PIB : 400147210003
JIB : 4400147210003
Matični broj : 1809741

Upis u sudski registar br. 85-01-0075-08
Upisani i uplaćeni kapital : 2.925.686.00 KM

EORI number : SIBA005005LC03846

GATARIĆ

G R O U P

www.gataric.net
komercijala@gataric.net

Nova Banka Doboj
UniCredit Bank dd

5550080000786975
3383902266134247



Glue stick Technical Data - TTS 406792 / TTS 404288

Inspection details

Inspection Items	Standard Demand	Test result	Result
Appearance	Transparent or translucent liquid with no obvious impurities	Transparent and no impurities	Qualified
Solid Content	Put the sample in (23±2) °C, measured with a rotary viscometer ≥1200	1500	Qualified
Coating	Cut the A4 paper into (105±3) mm X (37±2) mm, Coat the glue stick on the part of paper (size is 90mm X 37mm) and press them smoothly. Put sample in temperature demand is (30±10) °C, humidity (60±15) % for 1 hour, then use your hands to evenly apply the peeling force on the uncoated part until the paper is broken.	the paper broken	Qualified
Cold Resistance	Put the 100ml samples in the (-15±5) °C fridge for 5 hours and take it out in the normal room temperature (20±15) °C. After the glass rod was stirred evenly, the glue was placed on the reverse side for 3 times, and the fluidity did not change significantly	up to the standard	Qualified
Heat Resistance	Put 100ml sample under the temperature of (50±2) °C for 5 hours, and immediately detected after removal, no obvious changes in agglomeration and stratification.	up to the standard	Qualified
Non-volatile Matter Content	≥8	9.8	Qualified
PH Value	6-8	6.35	Qualified

Date: March 2023

